

SUPERWALL

APPLICATION

Superwall is a BBA approved dual purpose cavity wall slab. Treated with water repellent additives, Superwall is intended for new masonry walls in either Full Fill or Partial Fill applications.

PRODUCT INFORMATION	
Thickness	50 – 100 mm
Length	1200 mm
Width	455 mm
Thermal Conductivity	0.036 W/mK
Product Designation	MW-EN13162-T2
Reaction to fire classification group	A1

SUITABLE FOR



MASONRY WALLS

See also:

White Blowing Wool
Yellow Blowing Wool

SPECIFICATIONS

THICKNESS (mm)	R-VALUE (m ² K/W)	SLABS/ PACK	PACK AREA (m ²)	PRODUCT CODE
50	1.35	16	8.74	5267
65	1.80	12	6.55	5268
75	2.05	10	5.46	5269
85	2.35	9	4.91	5270
100	2.75	8	4.37	5271



ENVIRONMENTAL

Superwall is made from fine non-combustible mineral wool (as defined in BS 3533:1981) and complies with BBA Specification (Cert. No. 89/2231). The layers of bonded, water repellent treated glass wool are formed into resilient slabs using a resin binder. All Superglass products are made from natural materials and recycled glass. They are CFC and HCFC free, will not rot, degrade or sustain vermin and will not encourage the growth of mould or fungi. The BBA Agrément Certificate is available on request or from the BBA Website www.bbacerts.co.uk.

HEALTH AND SAFETY

All Superglass products are subject to a Workplace Exposure Limit (WEL) 5 mg/m³ 8 hour Time Weighted Average Gravimetric Measure. A COSHH sheet (Ref AS001) and Material Safety Data Sheet (Ref AS002) can be obtained from Superglass Technical Department. Further reference can be made to EURISOL's Health & Safety Statement which can be found at www.eurisol.com.

SUPERWALL

BRITISH STANDARDS

Superwall is manufactured to comply with the requirements of the EU Construction Product Directive (89/106/EEC) and Technical European Harmonised Standards BS EN 13162:2001, BS EN 13172:2001 for Factory Made Mineral Wool Products. Suitable for the conditions in which it is intended.

FIRE PERFORMANCE

Superwall is classified as non-combustible with a Reaction to Fire Classification A1 when tested to BS EN 13501-1.

VAPOUR RESISTANCE

Superglass products possess negligible vapour resistance allowing vapour to pass freely through the insulation.

TEMPERATURE LIMITATION

Superglass mineral wool has a limiting temperature of 540°C, though with temperatures in excess of 230°C partial loss of the binder may occur at the hot face. This does not impair the thermal performance of the product.

PACKAGING

Superwall is supplied compression packed in polythene.

STORAGE

Superglass products must be stored indoors or under a waterproof covering in order to protect against weather damage.

Sales Office

E Mail: sales@superglass.co.uk
Tel: 01786 402014
Fax: 01786 451245

The office hours are Monday to Friday 8.30am to 5.00pm.

Technical Support

E Mail: technical@superglass.co.uk
Tel: 01786 402018
Fax: 01786 402029

Full product information is also available on CD Rom or can be downloaded from our web site.

SUPERGLASS CERTIFICATION



FM 02264

INDUSTRY BODIES



EURISOL
EXCELLENCE IN INSULATION



Superglass Insulation Limited

Thistle Industrial Estate
Kerse Road Stirling Scotland FK7 7QQ

Tel: 01786 451170
Fax: 01786 451245

www.superglass.co.uk